



## ***Application Guidelines 2200-15 Elastomeric Wall Coating***

*The AcryLabs 2200-15 Elastomeric Wall Coating is a membrane designed for masonry surfaces such as block, stucco and Dry-Vit. Combining successive coats of the 2200 (100% Acrylic/Elastomeric) coating creates a breathable membrane with superior weatherability. The 2200-15 is a monolithic, sustainable system that will yield a final minimum membrane thickness of 15 mils throughout the substrate. AcryLabs coatings are waterborne and meet or exceed all V.O.C. regulatory requirements.*

| <u>Integral Components of the 2200-15 System</u> | <u>Primers and Accessory Items</u> |
|--|------------------------------------|
| 2200 Elastomeric Wall Coating                    | 2400 Brush Grade Acrylic Sealant   |
|  | 3300 Clear Acrylic Primer          |

### ***Installation:***

#### **1.) Preparation**

AcryLabs coatings are adhesive and require a clean, dry surface to ensure proper adhesion. The key to successful coating application is preparation. Pressure washing is the preferred method for removing all oxidation, dirt and contaminants. When pressure washing is not appropriate, consult AcryLabs Inc.'s Technical Department for additional information.

#### **2.) Repair**

The applicator needs to provide a sound substrate for the 2200-15 system. All repairs should be made following industry guidelines. These materials should not be applied over mildew or damaged surfaces. If any unusual conditions exist, consult AcryLabs, Inc.'s Technical Department.

### **3.) Field Application**

Apply 2200 Elastomeric Wall Coating to all areas at a minimum rate of 1 gallon per 100 square feet. Allow to dry. Apply final coat 2200 Elastomeric Wall Coating to all areas at a minimum rate of 1 gallon per 100 square feet.

\*When spraying, be sure to back roll to avoid lap marks or streaking.

### **4.) Inspection**

Inspect walls and apply additional AcryLabs coating as necessary to insure a final membrane thickness of 15 mils DFT (dry film thickness) throughout the substrate.

This is a general guideline. Minimum material requirements may change based on project specifications. Consult AcryLabs' Technical Department for additional information. Failure of the substrate does not constitute AcryLabs coating or system failure.

#### **Application:**

AcryLabs coatings can be brushed, rolled or sprayed utilizing airless spray equipment.

**Spray Equipment:** The following are guidelines for airless equipment:

2500PSI                      2 gallons per minute                      Tips: 427-433

#### **Warranty:**

AcryLabs' responsibility under this limited warranty is for defective material. AcryLabs, Inc.'s only obligation is either to replace material or refund the price of materials proven defective.