



## Liquid Roofing Products

### Application Guidelines

# **Acrylabs DEK-coat Deck System** ***Acrylabs Liquid Applied Roof Membrane – Systems***

---

***New Construction:*** After installing plywood, patch screw holes, wide gaps, damaged edges, etc. with Acrylabs Brushable Sealant to achieve a smooth surface.

Apply 4" Fabric Reinforcement embedded and saturated with Acrylabs Base Coat to all plywood seams.

Apply suitable sized fabric embedded and saturated with Base Coat to act as flashing at perimeter, penetrations, and critical areas.

Apply 40" wide Fabric Reinforcement embedded and saturated with Base Coat to field of deck.

Allow all Base Coat and Fabric application to dry.

Apply two coats of Acrylabs DEK-coat to all areas including flashings. Allow to dry between coats. (Note: For best results apply DEK-coat finish coats at 90 degrees to each other so as to create a cross-hatch pattern.)

***Existing Deck Surface:*** Power wash existing deck with 3500 - 4000psi power washer to remove all dirt and contaminates.

Apply suitable sized fabric embedded and saturated with Base Coat to act as flashing at perimeter, penetrations, and critical areas.

Apply 40" wide Fabric Reinforcement embedded and saturated with Base Coat to field of deck.

Allow all Base Coat and Fabric application to dry.

Apply two coats of Acrylabs DEK-coat to all areas including flashings. Allow to dry between coats. (Note: For best results apply DEK-coat finish coats at 90 degrees to each other to create a cross-hatch pattern.)