



## Liquid Roofing Products

### Application Guidelines

#### ***Liquid Walk Pad*** ***Acrylabs Liquid Applied Roof Membrane - Systems***

---

The Acrylabs Liquid Walk Pad is a textured membrane designed for wood, metal, E.P.D.M.(rubber) and most existing traditional roofing materials as well as cementitious surfaces. Whether applying a single coat or combining multiple coats, Acrylabs Liquid Walk Pad creates a fully adhered, breathable membrane with superior weatherability and non-slip characteristics for walking safety and traffic management on most roofing surfaces. Liquid Walk Pad is a monolithic, sustainable system that will yield a range of a final minimum membrane thickness of 10-20 mils throughout the substrate. Milage will vary greatly depending on desired non-skid coarseness. Acrylabs coatings are waterborne and meet or exceed all V.O.C. regulatory requirements.

Integral Component	Primers and Accessory Items
Liquid Walk Pad Roof Coating Fabric Reinforcement	Brush Grade Acrylic Sealant Clear Acrylic Primer

### **Installation:**

#### **1.) Preparation**

Acrylabs coatings are adhesive and require a clean, dry surface to ensure proper adhesion. The key to a successful coating application is preparation. Pressure washing is the preferred method for removing all oxidation, dirt, and contaminants.

#### **2.) Repair**

A sound substrate is required for the Acrylabs Liquid Walk Pad. All repairs should be made following industry guidelines. These materials should not be applied over mildew or damaged surfaces.

### **3.) Field Application**

Carefully tape off desired walking locations, apply Acrylabs Liquid Walk Pad with-in taped areas at a minimum rate of 1 gallon per 30-50 square feet. Allow to dry. Apply final coat of Acrylabs Liquid Walk Pad to all areas at a minimum rate of 1 gallon per 30-50 square feet. Product coverage rate and mil thickness will vary due to substrate variables and desired coarseness.

### **4.) Inspection**

Inspect walls and apply additional Acrylabs coating as necessary to insure a final membrane thickness of 15-20 mils DFT (dry film thickness) throughout the substrate.

This is a general guideline. Minimum material requirements may change based on project specifications. Failure of the substrate does not constitute Acrylabs coating or system failure.

### **5.) Application**

Acrylabs Liquid Walk Pad can be applied with either a foam core cover or ¼" nap up to a 1" nap roller cover depending on desired coarseness.

### **6.) Spray Equipment**

Not Applicable

Consult Acrylabs Technical Department for additional information.