



Liquid Roofing Products

Application Guidelines

Finish Coat – Wall Coating ***Acrylabs Liquid Applied Roof Membrane - Systems***

The Acrylabs Finish Coat is designed for many surfaces including masonry surfaces such as brick, block, stucco EIFS, metal panels, wood, cement board, previously painted surfaces and more. Combining multiple coats of the Acrylic Finish Coat creates a breathable membrane with superior weatherability. Applying multiple coats of the Acrylabs Finish Coat creates a monolithic, sustainable protective membrane that will yield a final minimum thickness of 16-20 mils throughout the substrate. Acrylabs coatings are waterborne and meet or exceed all V.O.C. regulatory requirements.

Component	Accessory Items
Acrylabs Finish Coat	Base Coat Fabric Reinforcement Brushable Sealant

Installation:

1.) Preparation

Acrylabs Finish Coat is an adhesive and require a clean, dry surface to ensure proper adhesion. The key to a successful coating application is preparation. Pressure washing is the preferred method for removing all oxidation, dirt, and contaminants.

2.) Repair

A sound substrate is required for the wall coating to perform as expected. All repairs should be made following industry guidelines. These materials should not be applied over mildew or damaged surfaces.

3.) Field Application

Apply Acrylabs Finish Coat to all areas at a minimum rate of 1 gallon per 100 square feet. Allow to dry. Apply final coat of Acrylabs Finish Coat to all areas at a minimum rate of 1 gallon per 100 square feet. Product coverage rate and mil thickness will vary due to substrate variables.

When spraying, be sure to back roll to avoid lap marks, streaking and uniformity.

4.) Inspection

Inspect walls and apply additional Acrylabs Finish Coat as necessary to insure a final membrane thickness of 16-20 mils DFT (dry film thickness) throughout the substrate.

This is a general guideline. Minimum material requirements may change based on project specifications. Failure of the substrate or previously coated areas does not constitute Acrylabs coating or system failure.

5.) Application

Acrylabs' coatings can be brushed, rolled, or sprayed utilizing airless spray equipment.

6.) Spray Equipment

A minimum 3000 PSI airless pump is required. Tips range: 320-630

Consult Acrylabs Technical Department for additional information.